

Test Report No.: SDHG1312013099FB Date: Dec.16, 2013 Page 1 of 4

REKE TRADING ADRESS: ORTHEN 191 ZIPCODE: 5231 XR CITY: DEN BOSCH

COUNTRY: THE NETHERLANDS

THE ATTENTION OF: MR. RENE VAN GERVEN

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : PVC TENT FABRIC SGS Ref No. : 201311000197 Sample Receiving Date : Dec.04, 2013

Test Performing Date : Dec.04, 2013 to Dec.16, 2013

Test Result Summary

| No. | Test(s) Requested | Result(s) | Comments | | | |
|--|-------------------|-----------------------|----------|--|--|--|
| 1 | NF P 92-507:2004 | Classification: M2 | / | | | |
| For further details, please refer to the following page(s) | | | | | | |

Note: The classes with their corresponding fire performance are given in Annex I.

Signed for and on behalf of SGS-CSTC Co., Ltd.

Irvette Zhang Approved signatory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions



Test Report No.: SDHG1312013099FB Date: Dec.16, 2013 Page 2 of 4

I. Test conducted

This test was conducted according to NF P 92-507:2004 Fire safety-building-interior fitting materials -Classification according to their reaction. And the test methods as following:

1. NF P 92-503:1995 Safety against fire - Building materials - Reaction to fire tests - Electrical burner test used for flexible materials

II. Details of classified product

The details of the tested specimen given below have been prepared from information provided by the sponsor of the test. All values quoted are nominal, unless tolerances are given.

| Sample description | PVC TENT FABRIC | | |
|--------------------|----------------------|--|--|
| Color | White | | |
| Area density* | 490 g/m ² | | |
| Thickness* | Approximately 0.4 mm | | |

^{*---}Measured by the laboratory

III. Conditioning

Prior to testing, the sample was conditioned,

In an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5% until constant mass is obtained. The mass is considered as constant when two successive weightings 24 hours apart do not differ by more than 0.1% or 0.1 g (take the highest mass value).

To be continued...

中国·广东·佛山市振撼区大良街道办事处五沙版和南西1号欧洲工业园一号厂房首园 雏编:528333 t (86-757)22805888 t (86-757)22805858 e sgs.china@sgs.com

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.egs.



Test Report No.: SDHG1312013099FB Date: Dec.16, 2013 Page 3 of 4

IV. Test results

i) NF P92-503:1995 Electrical burner test

| | Specimen 1 | Specimen 2 | Specimen 3 | Specimen 4 | AVE |
|--|------------|------------|------------|------------|-----|
| The length of inflammation after withdrawing the pilot flame (seconds) | 9 | 13 | 14 | 14 | |
| The white-hot points with or without propagation effects | No | No | No | No | |
| The maximum limit distance of charring or destruction (mm) | 178 | 190 | 200 | 195 | |
| The maximum width of charring of each test piece found between 450mm and 600mm from its lower edge(mm) | 0 | 0 | 0 | 0 | 0 |
| Flaming drops or debris (Yes/No) | No | No | No | No | |
| Burn through (Yes / No) | Yes | Yes | Yes | Yes | |

Statement:

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product, which is supplied or used, is fully represented by the specimens, which were tested.

To be continued...

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-



Test Report No.: SDHG1312013099FB Date: Dec.16, 2013 Page 4 of 4

Annex I, Requirements

Table 1: Resume of classification for the and flexible materials which thickness no more than 5mm

| Test Items | Criteria of classification | | | | |
|---|----------------------------|--------------------------------|-------------------------|-----------------------------|-------------------------|
| Test for hot melt materials | | Not ignite the wadding | Not ignite the wadding | Ignite the wadding | Ignite the wadding |
| Electrical burner test a | No drops | Non-flaming molten droplets | Flaming drops or debris | Non-flaming molten droplets | Flaming drops or debris |
| Flame persistence time ≤ 5s | M1 | M1 | M2 | M4 | M4 |
| Flame persistence time > 5s, and average distance of charring or destruction < 350mm | M2 | M2 | МЗ | M4 | M4 |
| Flame persistence time > 5s, and average width of charring found between 450mm and 600mm from specimen's lower edge < 90mm | МЗ | МЗ | M4 | M4 | M4 |
| Flame spread test (< 2mm/s) | | | M4 | M4 | M4 |

a) If the materials presented a particular behaviour, the classification also needs to refer to Table 3. For the classification M0 refer to clause 3.3

Photo Appendix:



End of Report

icity of testing (inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN_Doccheck@sgs.com

> 16, Faliding Engren intustrial Part No.1 Sturtenum Rest Water Sedon Dalang Town, Sturder Forter, Guargiang Dines 528333 t (86-757) 22805888 f (86-757) 22805888 www.sgsgroup.com.cn 中国·广东·佛山市振荡区大良街道办事处五沙叛和南西1号欧洲工业园一号广房首层 单编;528333 t (86-757)22805888 t (86-757)22806858 e sgs.china@sgs.com